

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 60118618
PUBLICATION DATE : 26-06-85

APPLICATION DATE : 25-11-83
APPLICATION NUMBER : 58222358

APPLICANT : NIPPON PILLAR PACKING CO LTD;

INVENTOR : MAEDA TOSHIHISA;

INT.CL. : C01B 31/04

TITLE : METHOD FOR DECREASING RESIDUAL SULFUR CONTAINED IN EXPANDED GRAPHITE

ABSTRACT : PURPOSE: To enable the removal of sulfur from expanded graphite, easily and effectively, by oxidizing the expanded graphite containing residual sulfur with air in a specific air atmosphere.

CONSTITUTION: An expanded graphite containing residual sulfur is exposed to the atmosphere composed of air flowing at a rate of 0.1~10 liter/min 1g of the expanded graphite, at 400~650°C for 0.2~15hr, to effect the oxidation of the expanded graphite with air. Usually, an expanded graphite contains about 800~ 6,000ppm of residual sulfur, however, the sulfur content can be reduced to about 0~300ppm by the above process. The problem of the apparatus corrosion can be solved nearly completely at a maximum sulfur content of about 300ppm. When the expanded graphite is used in the application such as solid catalyst for which the presence of impurities is absolutely prohibited, it is necessary to keep the residual sulfur to 0ppm, and it can be achieved by carrying out the above air- oxidation process under controlled condition.

COPYRIGHT: (C) JPO